



SCL ANTI-TAG COATING SYSTEM **PLAIN COLOUR SPECIFICATION**

Scope of Works: External - bare, porous masonry surfaces

Before work commences ensure all health and safety data sheets are read and understood.

Introduction

All working practices to be carried out in strict accordance with BS8000: 1989 Workmanship on building sites Part12 Code of Practice for decorative wallcoverings and painting.

This specification is for the use of technically competent personnel and must be read in conjunction with the relevant product data sheets prior to surface preparation and application.

All material coverage rates stated are theoretical and are based on covering smooth non-porous surfaces. Practical coverage rates can be affected by surface texture, surface porosity and material wastage.

Surface Preparation

Remove existing graffiti where possible with SCL Scrubs Graffiti Remover Wipe System or SCL Wipe-off Graffiti Remover as appropriate. If any remaining graffiti causes pigment bleed-through after the application of the primer, remedial action should be taken prior to the application of SCL Anti Tag Finish.

Wash down with SCL Wash Down Agent and rinse thoroughly with clean water.

Ensure prepared surface is clean, dry and sound, free from grease, oils or other surface contaminants.

If moss, fungi, lichen or mould is or has been present, treat affected area with SCL Anti-Fungicidal Wash.

Ensure surface is fully cured and is dry to a protimeter reading of within the solid green section on the top scale (Ref: Protimeter Surveymaster).

SEAMLESS COATINGS LIMITED

Unit 18 Oak Street Industrial Estate, Cradley Heath, West Midlands B64 5JY

Tel: 01384 413 815 Website: www.seamlesscoatings.co.uk E-Mail: sales@seamlesscoatings.co.uk



Coating Specification: SCL Anti Tag Coating System Plain Colour

By brush or short/medium pile roller, apply one full coat of SCL Masonry Sealer at a coverage rate of 10m² per litre.

Allow to cure.

Overcoating time: minimum 16 hours, maximum 48 hours.

By brush or short/medium pile roller, apply one full coat of SCL Masonry Primer at a coverage rate of 12m² per litre.

Allow to cure.

Overcoating time: minimum 16 hours, maximum 48 hours.

By brush or short/medium pile roller, apply one full coat of SCL Anti Tag Finish (gloss or satin) at a coverage rate of 10m² per litre per coat.

Allow first coat to cure then repeat process for a second full coat.

Overcoating time: minimum 8 hours, maximum 48 hours.

Note:

Drying/curing times will be shortened by higher temperatures and lengthened by lower temperatures

Coverage rates of all materials will vary according to weather conditions, dimensions and nature/condition of substrates. Make appropriate allowances where applicable