



SCL 95 Cladding Finish

CLADDING FINISH

EXTERIOR PROTECTION OF CONCRETE
AND STEEL STRUCTURES

Intended uses

A high performance, hardwearing colour stable top coat for long term exterior protection of concrete and steel structures, roofs, cladding etc.

Product description

SCL95 Cladding Finish is a durable semi-gloss high build coating specially designed for the cost-effective refurbishment of metal sheets and vertical cladding.

Product information

Product reference	SCL 95
Volume solids	70%
Typical thickness	70 microns dft from 100 microns wet
Theoretical coverage	7m ² per litre per coat
Practical coverage	Reduce by 20% or more
Appearance/ colour range	Semi Gloss/White and selected BS4800 colours
VOC content	EU Limit value for this product: (Cat A/I):600g/l (2007) 500g/l (2010). This product contains a maximum of 300g/l



Application details

Mix ratio	N/A
Method of application	Brush or airless spray. Apply two coats over primed surfaces ensuring good edge coverage.
Thinner	SCL Solvent
Cleaner	SCL Solvent
Pot life	N/A
Drying time:	
Substrate temperature	20°C
Touch dry	3 hours
Hard dry	12 hours
Minimum overcoating interval	8 hours
Maximum overcoating interval	48 hours

Note: Drying/curing times will be shortened by higher temperatures and lengthened by lower temperatures

Storage & handling

Storage	Store the closed containers in a safe place out of reach of children
Pack size	5 litres
Flash point	Approximately 40°C
Product	Approximately 1.25kg per litre
Shelf life	6 months in unopened containers stored in dry moderate temperatures

Surface preparation

Ensure surfaces are sound, clean, dry, properly prepared and primed/undercoated as required depending on substrate.

Limitations

Do not use personnel who are asthmatic to apply these products, especially in confined spaces.

Application of excessive material may result in down glossing and other film defects.

Must be overcoated within 48 hours otherwise sanding and/or solvent washing may be required in order to maintain intercoat adhesion.

Safety precautions

A copy of the appropriate health & safety data sheet should be consulted prior to using the product. This can be faxed if urgently required.

Minimum precautions for all paints:

1. Avoid skin and eye contact i.e wear gloves, goggles, etc
2. Ensure good ventilation, mechanical if necessary
3. Store and use away from heat and flame
4. Do not eat or smoke in the vicinity of work
5. Wash hands before eating



Definitions

Tolerances All information quoted in this data sheet is subject to normal manufacturing tolerances

Practical coverage Practical coverage can vary considerably depending on method of application, surface roughness, weather conditions and complexity of the structure

Pot life Applies only to two component products and refers to the time the mixture remains usable

Technical support

If you would like any information on SCL products please call: **01384 413815** or email us at: **sales@seamlesscoatings.co.uk**

Disclaimer

The information contained herein is to the best of our knowledge true and accurate and is given in good faith, but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Seamless Coatings be liable for consequential or incidental damages.

Seamless Coatings Ltd

Unit 18, Oak Street Industrial Estate, Cradley Heath, West Midlands B64 5JY **Office:** 01384 413815 **Fax:** 01384 413830

www.seamlesscoatings.co.uk